

ECO-DRY COOL+

| | | |
|-----------------------------------------------|---------------------------------------------------|-----------------------------------------------------------|
| Uses | Liner - Firefighter | |
| Quality and Finish | Hainsworth® Eco Dry Cool + | |
| Colour | Paris / Ecu | |
| Composition | 65% Nomex® 35% Wool/Lenzing | |
| Construction | Plain Weave Rip Stop | |
| Conditioned Weight (gsm) | 135 +/- 5% | BS EN12127 |
| Useable Width (cms) | ≥ 160 | BS EN 1773:1997 |
| Tensile Strength Warp / Weft N | ≥ 700 / 240 | BS EN ISO 13934-1 |
| Tensile Extension Warp / Weft % | ≥ 40 / 10 | BS EN ISO 13934-1 |
| Tear Strength Warp / Weft N | ≥ 30 / 20 | BS EN ISO 13937-2 |
| Washing Stability Warp / Weft % | ≤ 3 | ISO 5077 after 5 cycles To ISO 6330 (2A Pro E) |
| Abrasion Resistance 12KPa 2 Broken Threads | ≥ 50,000 | ISO 12947-2 |
| Pilling | ≥ 4 | BS EN ISO 12945-2 4000 Cycles |
| Colour Fastness to Light | ≥ 3 | BS EN ISO 105 B02 |
| After Care | Wash at 60C Tumble Dry Hot - Do not bleach | |



HAINSWORTH®
TECHNOLOGY

Spring Valley Mills, Stanningley, Pudsey, West Yorkshire LS28 6DW United Kingdom

hainsworthtechnology.co.uk

