

# TITAN 1250

Uses	<b>Outer Shell - Firefighter</b>	
	<b>Single Layer Coverall - Police</b>	
Quality and Finish	<b>TITAN 1250 Repel+</b>	
Colour	<b>Paris Blue</b>	
Composition	<b>59% Nomex® 40%Kevlar® 1%P140</b>	
Construction	<b>Plain Weave Rip Stop Double Cloth</b>	
Conditioned Weight (gsm)	<b>270 +/- 5%</b>	<b>BS EN12127</b>
Useable Width (cms)	<b>≥ 160</b>	<b>BS EN 1773:1997</b>
Tensile Strength Warp / Weft N	<b>≥ 2000 / 2000</b>	<b>BS EN ISO 13934-1</b>
Tensile Extension Warp / Weft %	<b>≥ 12 / 10</b>	<b>BS EN ISO 13934-1</b>
Tear Strength Warp / Weft N	<b>≥ 300 / 300</b>	<b>BS EN ISO 13937-2</b>
Washing Stability Warp / Weft %	<b>≤ 3</b>	<b>ISO 5077 after 5 cycles To ISO 6330 (2A Pro E)</b>
Abrasion Resistance 12KPa 2 Broken Threads	<b>≥ 40,000</b>	<b>ISO 12947-2</b>
Pilling	<b>≥ 3-4</b>	<b>BS EN ISO 12945-2 4000 Cycles</b>
Flammability: Limited Flame Spread	<b>Index 3</b>	<b>EN ISO 15025 Method A</b>
Colour Fastness to Light	<b>≥ 6</b>	<b>BS EN ISO 105 B02</b>
Water Repellency	<b>&gt; 4</b>	<b>EN 24920</b>
After Care	<b>Wash at 60C Tumble Dry Hot - Do not bleach</b>	

\*Technical Specifications above relate to TITAN 1250 Paris Blue, specific details for other colours of TITAN 1250 are available on request from [sales@hainsworthtechnology.co.uk](mailto:sales@hainsworthtechnology.co.uk).



**HAINSWORTH®**  
TECHNOLOGY

Spring Valley Mills, Stanningley, Pudsey, West Yorkshire LS28 6DW United Kingdom

[hainsworthtechnology.co.uk](http://hainsworthtechnology.co.uk)

