

# TITAN 1260

Uses	<b>Outer Shell - Firefighter</b>	
Quality and Finish	<b>TITAN 1260 Repel+</b>	
Colour	<b>Black Gold</b>	
Composition	<b>5% Para-Aramid 23% Meta-Aramid 70% PBI Proprietary Blend 2% Antistatic</b>	
Construction	<b>Plain Weave Rip Stop</b>	
Conditioned Weight gsm	<b>220 +/- 5%</b>	<b>BS EN12127</b>
Useable Width cms	<b>≥ 160</b>	<b>BS EN 1773:1997</b>
Tensile Strength Warp / Weft N	<b>≥ 2000 / 2000</b>	<b>BS EN ISO 13934-1</b>
Tensile Extension Warp / Weft %	<b>≥ 18 / 7</b>	<b>BS EN ISO 13934-1</b>
Tear Strength Warp / Weft N	<b>≥ 165 / 165</b>	<b>BS EN ISO 13937-2</b>
Washing Stability Warp / Weft %	<b>≤ 3</b>	<b>ISO 5077 after 5 cycles To ISO 6330 (2A Pro E)</b>
Abrasion Resistance 12KPa 2 Broken Threads	<b>≥ 30,000</b>	<b>ISO 12947-2</b>
Pilling	<b>≥ 4</b>	<b>BS EN ISO 12945-2 4000 Cycles</b>
Flammability: Limited Flame Spread	<b>Index 3</b>	<b>EN ISO 15025 Method A</b>
Colour Fastness to Light	<b>≥ 5</b>	<b>BS EN ISO 105 B02</b>
Water Repellency	<b>&gt; 4</b>	<b>EN 24920</b>
After Care	<b>Wash at 60C Tumble Dry Hot - Do not bleach</b>	

\*Technical Specifications above relate to TITAN 1260 Black Gold, specific details for other colours of TITAN 1260 are available on request from sales@hainsworthtechnology.co.uk.



**HAINSWORTH<sup>®</sup>**  
TECHNOLOGY

Spring Valley Mills, Stanningley, Pudsey, West Yorkshire LS28 6DW United Kingdom

**hainsworthtechnology.co.uk**

