

ECO-DRY SHIELD

Uses	Single Layer PPE - Wildland Firefighter or Station Wear	
Quality and Finish	Hainsworth® Eco Dry Shield	
Colour	Paris Blue, Yellow, Lime Green, Flame Red, Orange	
Composition	72% Meta-aramid / Para-aramid / Antistatic (93/5/2) 28% Wool / Lenzing (50/50)	
Construction	Twill	
Conditioned Weight (gsm)	240 +/- 5%	BS EN12127
Useable Width (cms)	≥ 160	BS EN 1773:1997
Tensile Strength Warp / Weft N	≥ 1300 / 700	BS EN ISO 13934-1
Tensile Extension Warp / Weft %	≥ 40 / 15	BS EN ISO 13934-1
Tear Strength Warp / Weft N	≥ 80 / 120	BS EN ISO 13937-2
Washing Stability Warp / Weft %	≤ 3	ISO 5077 after 5 cycles To ISO 6330 (2A Pro E)
Abrasion Resistance 12KPa 2 Broken Threads	≥ 30,000	ISO 12947-2
Flammability: Limited Flame Spread	Index 3	EN ISO 15025 Method A
Colour Fastness to Light	≥ 5	BS EN ISO 105 B02
Colour Fastness to Rubbing	≥ 4	BS EN ISO 105 X12
Colour Fastness to Water	> 4	BS EN ISO 105 E01
After Care	Wash at 60C Tumble Dry Hot - Do not bleach	



HAINSWORTH® PROTECTIVE FABRICS

Spring Valley Mills, Stanningley, Pudsey, West Yorkshire LS28 6DW United Kingdom

hainsworthprotectives.co.uk

