

TITAN 1241

| | | |
|---|--|---|
| Uses | Outer Shell - Police | |
| | Outer Shell - Technical Rescue & EMS | |
| Quality and Finish | TITAN 1241 Repel+ | |
| Colour | Paris Blue | |
| Composition | 87% Meta-aramid 11% Para-aramid 2% Antistatic | |
| Construction | Plain Weave Rip Stop | |
| Conditioned Weight (gsm) | 175 +/- 5% | BS EN12127 |
| Useable Width (cms) | ≥ 160 | BS EN 1773:1997 |
| Tensile Strength Warp / Weft N | ≥ 800 / 750 | BS EN ISO 13934-1 |
| Tensile Extension Warp / Weft % | ≥ 40 / 30 | BS EN ISO 13934-1 |
| Tear Strength Warp / Weft N | ≥ 45 / 70 | BS EN ISO 13937-2 |
| Washing Stability Warp / Weft % | ≤ 3 | ISO 5077 after 5 cycles To ISO 6330 (2A Pro E) |
| Abrasion Resistance 12KPa 2 Broken Threads | ≥ 55,000 | ISO 12947-2 |
| Pilling | ≥ 3-4 | BS EN ISO 12945-2 4000 Cycles |
| Flammability: Limited Flame Spread | Index 3 | EN ISO 15025 Method A |
| Colour Fastness to Light | ≥ 6 | BS EN ISO 105 B02 |
| Water Repellency | > 4 | EN 24920 |
| After Care | Wash at 60C Tumble Dry Hot - Do not bleach | |

*Technical Specifications above relate to TITAN 1241 Paris Blue, specific details for other colours of TITAN 1241 are available on request from sales@awhainsworth.co.uk.



HAINSWORTH®
PROTECTIVE FABRICS

Spring Valley Mills, Stanningley, Pudsey, West Yorkshire LS28 6DW United Kingdom

hainsworthprotectives.co.uk

